



DTF INSTRUCTIONS

- PRESSURE:** MEDIUM (60 LBS)
- GENERAL SETTINGS:** POLYESTER- 275 DEGREES/10 SECONDS
TRIBLEND- 275 DEGREES/10 SECONDS
COTTON- 325 DEGREES/15 SECONDS
50/50- 300 DEGREES/12 SECONDS
*THICKER FABRIC MAY REQUIRE HIGHER HEAT
- PEEL:** WARM-COLD (WAIT 10-20 SECONDS BEFORE PEELING)
- FINISHING:** MATTE FINISH - REPRESS 5-10 SECONDS W/
ROUGHER TEXTURE COVER SHEET OR KRAFT PAPER
GLOSS FINISH - REPRESS 5-10 SECONDS W/TEFLON SHEET

*****DISCLAIMER*****

THESE ARE GENERAL SETTINGS AND YOUR SETTINGS MAY VARY. PLEASE DO YOUR OWN TESTING TO SEE WHAT WORKS BEST FOR YOUR EQUIPMENT AND GARMENTS. YOU MUST USE A FULL SIZE HEATPRESS - EASY PRESSES MAY NOT WORK WITH DTF.

**EMAIL CUSTOM DTF ORDERS TO:
ORDERS@AAVINYL.COM**